



EZ-TIGHT COMPRESSION GASKET

anaco • 1001 El Camino Ave., Corona, CA 92879 • (951) 372-2732

Description:

Ez-Tight is a one-piece compression gasket. It is used for joining hub and spigot cast iron soil pipe and fittings made according to ASTM A74.

Gasket Specifications:

Ez-Tight gaskets conform strictly to ASTM Standard C564, latest issue.

Joint Characteristics:

Gasket joints will not leak even if deflected as much as 5 degrees, or when subjected to vibration, seismic tremors, expansion, contraction, external or internal test pressure.

Bracing:

To prevent movement, horizontal pipe and fittings 5" and larger should be suitably braced by the use of blocks, rdding or other suitable methods at every branch or change of direction.

Test:

For best results, test one floor (ten feet) at a time. The system should be properly restrained; all bends, changes of direction and ends of runs should be restrained.

Gasket Material:

Ez-Tight gaskets are made of Neoprene as the sole elastomer. The physical characteristics of the Neoprene ensure that the gasket will not decay or deteriorate from contact with effluents in the pipe or chemicals in the soil or air around the pipe.



Size	Unit	Carton	Weight
2	.3	60	18
3	.4	40	16
4	.6	40	24
5	1.2	30	35
6	1.4	30	40

How to specify:

All 2-inch through 6-inch hub and spigot cast iron soil pipe and fittings shall conform to ASTM A74; joints shall be made either by caulked lead and oakum or by compression gaskets which conform to ASTM C564.

Hardness (nominal durometer ± 5) as specified by the pipe manufacturer	50	60	70	D2240
Elongation, min, percent	350	300	250	D412
Tensile strength, min, psi (MPa)	1500 (10)	1500 (10)	1500 (10)	D412
Tear Resistance, min, lbf/in. (N/cm)	150 (268)	150 (268)	150 (268)	D624
Compression set, max, percent	25	25	25	D395
Heat aging, 96 h at 158° \pm 2° F (70° \pm 1° C)				D573
Hardness, increase, max, durometer points	10	10	10	—
Loss in tensile strength, max, percent	15	15	15	—
Loss in elongation, max, percent	20	20	20	—
Water absorption: Weight increase, max, percent	20	20	20	D471 —
Ozone resistance	no cracks	no cracks	no cracks	D1149
Oil Immersion Volume increase, max, percent	80	80	80	D471